



0.025mm to 21mm (.001" to .827")



Order 3m to 3t (10 ft to 6000 Lbs)



Delivery: within 3 weeks



Wire to your spec



E.M.S available



Technical support

- Shaped wire
- Rope/Strand

Packaging

- Coils
- Spools
- Bars or lengths







Chemical Composition			Specifications	Key Features	Typical Applications
Element	Min %	Max %	AMS 5688	Good mechanical properties and corrosion	Springs
С	-	0.12	ASTM A313 ASTM A580 BS 970 BS 2056	resistance	Engineered components
Mn	-	2.00			Wire mesh
		0.045			Wire cloth
Р	-	0.045			Hose braiding
S	-	0.03	Designations		
Si	-	1.00	W.Nr. 1.4310		
Cr	17.00	19.00	UNS 30200 AWS 160		
Ni	8.00	10.00			
Fe BAL					

Density	8.0 g/cm ³	0.289 lb/in ³	
Melting Point	1420 ℃	2590 °F	
Coefficient of Expansion	17.6 μm/m °C (20 – 100°C)	9.8 x 10 ⁻⁶ in/in °F (70 – 212 °F)	
Modulus of Rigidity	70.3 kN/mm²	10196 ksi	
Modulus of Elasticity	187.5 kN/mm²	27195 ksi	

Heat Treatment of Finished Parts							
Condition of sumplied by Alley Wive	Туре	Temperature		Time a (IIIv)	Cooling		
Condition as supplied by Alloy Wire		°C	°F	Time (Hr)	Cooling		
Annealed or Spring Temper	Stress Relieve	250	480	1	Air		

Properties							
Condition	Approx. tensile stren	gth	Approx. operating temperature				
Condition	N/mm²	ksi	°C	°F			
Annealed	600 – 800	87 – 116	-200 to +300	-330 to +570			
Spring Temper	1300 – 2200	189 – 319	-200 to +300	-330 to +570			

The above tensile strength ranges are typical. If you require different please ask.





